



KLINGER'sil C-8200

Specialist grade based on a unique blend of fibres with an acid resisting binder. Specifically designed for aggressive chemical environments.

The Klinger group has been recognised as the market leader in gaskets and sealing for over a century. Our research and development laboratories have investigated over 250 different fibre forms in the search for asbestos free alternatives. The search has resulted in a range of high quality and high performance asbestos free materials that have been proven in service

General Properties

- Resistant to most mineral acids
- Resistant to alkalis, ketones, aldehydes
- Resistant to many refrigerants
- Resistant to oils, fuels, hydrocarbons etc.
- 3xA anti-stick finish on both sides

Typical Applications

- Sulphuric Acid
- Ethylene Chloride
- Hydrochloric Acid
- Caustic duties
- Hydrocarbons
- Refrigerants

Availability

Sheeting (m): 2.0 x 1.5*, 1.5 x 1.0
Thickness (mm): 0.5, 0.75, 1.0, 1.5, 2.0, 3.0


* - Denotes standard sheet size



Certificate No. FM 10571



KLINGERsil C-8200



Application Guidelines

1. Usually satisfactory without reference.
2. Usually satisfactory, but suggest you refer to Klinger for advice
3. Caution: May be suitable but essential that you refer to Klinger for advice.

Chemical compatibility must be considered in all cases.

Typical Specifications

Compressibility ASTM F 36 A		9%
Recovery ASTM F 36 A		55%
Klinger cold/hot compression (50MPa)	Thickness decrease 23°C	7%
	decrease at 300°C	17%
Gas leakage according to DIN 3535/6		<1.0ml/min
Chlorides (soluble)		150ppm
Thickness increase after fluid	H ₂ SO ₄ , 96% :18h/23°C	10%
Immersion ASTM F 146	HNO ₃ , 96% :18h/23°C	unsuitable
	H ₂ SO ₄ , 65% :48h/23°C	8%
Density		1.7g/cm ³
Average surface resistance	R _{OA} (xE9)	8.3 Ω
Average specific volume resistance	ρ _D (xE10)	1.2 Ω cm
Average power factor		17.5 kV/mm
Average dielectric strength	1kHz,ca. 3mm thick	0.27 tan δ
Average dielectric constant	1kHz,ca.3mm thick	8.4 ε _r

Head Office

KLINGER Ltd
Wharfedale Road
Euroway Trading Estate
Bradford BD4 6SG

Tel: 01274 688 222
Fax: 01274 688 549

Klinger Ltd. Grangemouth

Tel: 01324 472 231
Fax: 01324 482 111

Klinger Ltd. Runcorn

Tel: 01928 577 030
Fax: 01928 575 223

Klinger Ltd. Aberdeen

Tel: 01224 772 962
Fax: 01224 772 953

Klinger Ltd. International

Tel: 020 8308 0100
Fax: 020 8308 0200

Klinger Ltd. Middlesbrough

Tel: 01642 220 289
Fax: 01642 220 290

All information and recommendations contained in this specification sheet are to the best of our knowledge correct. Since conditions of use are beyond our control, users must satisfy themselves that the products are suitable for the intended processes and uses. No warranty is given or implied in respect of information or recommendations or that any use of products will not infringe rights belonging to other parties. In any event or occurrence our liability is limited to our invoice value of the goods delivered by us to you. We reserve the right to change product design and properties without notice